

ASTM D3577**455-2**

	surgical gloves	
	Elongation Before Aging	Elongation After Aging
Gloves compounded primarily from natural rubber latex.	750%, min	560%, min
Gloves compounded from a rubber cement or from synthetic rubber latex	650%, min	490%, min

Forza alla rottura dopo invecchiamento

9 N

6 N

ASTM D5250

Poly-vinyl chloride (PVC) gloves for medical application	300%	300%
--	------	------

3,6 N

ASTM D6319-10

Nitrile Examination Gloves for Medical Application	500%	400%, min
--	------	-----------

6 N

ASTM D3578

	Rubber Examination Gloves	
	Elongation Before Aging	Elongation After Aging
Gloves compounded primarily from natural rubber latex.	650%	500%

6 N

ASTM D 6124

Powder Free Gloves	≤ 2,0 mg/glove
Powdered Gloves	≤ 10,0 mg/dm ² - 120 mg/glove

EN 374-2- Penetrazione e livello di AQL: un guanto sottoposto a prove di tenuta all'aria e all'acqua, non deve presentare perdite e deve essere testato e controllato in conformità con il Livello medio di qualità (AQL). Livello 3 < 0.65 • Livello 2 < 1.5 • Livello 1 < 4.0	E' possibile apporre il pittogramma "Microorganismi" quando il guanto risulta conforme almeno alle specifiche di prestazione di livello 2 della prova di Penetrazione.
--	--